



Provisional Technical Datasheet

F03RR1 Polysure PP Homopolymer

BOPP Film

Product Characteristics:

Polysure F03RR1 is a Polypropylene Homopolymer, produced by latest Spheripol – II Technology & primarily suitable for BOPP tenter Process. F03RR1 combines narrow MFR specification range especially for consistent processing on high-speed BOPP lines. The grade is free from metal stearates making it suitable for metallisable BOPP film. This grade offers excellent stretchability & gel free films with superior clarity.

Recommended Applications:

General Purpose BOPP Films, Adhesive tapes, Food packaging, Textile overwraps, Metallisable BOPP Films & Lamination BOPP Films

Typical Properties:

Sr. No.	Property	Test Method	Unit	Value*
1	Melt Flow Index (230°C & 2.16 kg)	ASTM D1238	g/10 min	3.2
2	Tensile Strength at Yield, Type I Specimen	ASTM D638 (50 mm / min)	MPa	35
3	Tensile Elongation at Yield, Type I Specimen		%	12
4	Flexural Modulus (1% Secant)	ASTM D790A	MPa	1500
5	Notched Izod Impact Strength (23°C)	ASTM D256A	J/m	45
6	Vicat Softening Point (10 N)	ASTM D1525	°C	156
7	Heat Deflection Temperature (0.455 MPa)	ASTM D648	°C	95

*All the mechanical properties are tested on Injection molded Test Specimen, prepared in accordance with ASTM D4101

Processing Guidelines:

- Barrel Temperature : 230 - 280°C
- Quench Temperature : 10 - 15°C

Storage & Handling:

Bags should be stored in dry & dust free environment at temperature below 50°C and Prevent from direct exposure to sunlight & heat to avoid quality deterioration.

Regulatory Requirements:

F03RR1 to be manufactured complying the requirements specified in IS 10910 on "Specification for Polypropylene & its Copolymers for safe use in contact with Foodstuff, Pharmaceutical & Drinking water". Furthermore, the Additives added in this grade formulation compiles to the "Positive list of constituents for Polypropylene, Polyethylene and their Copolymers for its safe use in contact with Foodstuffs & Pharmaceuticals' as laid down under IS 16738:2018. In general, the additives & constituents used in the grade are in line with requirement laid down under FDA: CFR Title 21,177.1520, Olefin Polymers.

Updated as of May 2021

Disclaimer: The information & data presented herein are typical values & should not be considered as specification and may be used as guideline only. HMEL does not undertake any responsibility for any outcome or results from the adoption or replication of the above-mentioned data & information there on for possible use for various applications. HMEL reserves the right to change the information & data without any prior notice or information. The user will solely be responsible for any process/product usage.

HPCL-Mittal Energy Limited (HMEL), INOX Tower, Plot No.17, Sector-16A, Noida – 201301 (U.P), India. Tel: 0120-4634500. Corporate Site: www.hmel.in